


CARPENTER LTD CARPET UNDERLAY	INDIVIDUAL SPECIFICATION SHEET GLOSSOP PLANT	
Amendment:		Date: 22/05/09
EXTRASTEPE		
<p style="text-align: center;">CHARACTERISTIC</p> <p style="text-align: center;">ROLL LENGTH</p> <p style="text-align: center;">ROLL WIDTH</p> <p style="text-align: center;">DENSITY</p> <p style="text-align: center;">ROLL WEIGHT</p> <p style="text-align: center;">THICKNESS</p> <p style="text-align: center;">INTERNATIONAL COPDE FOR APPLICATION OF FIRE TEST PROCEDURES</p> <p style="text-align: center;">FLAMMABILITY (HOT METAL NUT TEST)</p> <p style="text-align: center;">THERMAL RESISTANCE</p> <p style="text-align: center;">IMPACT SOUND IMPROVEMENT INDEX</p> <p style="text-align: center;">DOUBLE STICK CASTOR WHEEL CHAIR TEST</p> <p style="text-align: center;">CLASSIFICATION</p>	<p style="text-align: center;">SPECIFICATION</p> <p style="text-align: center;">11 m min</p> <p style="text-align: center;">137cm ± 1%</p> <p style="text-align: center;">180Kg/m³ ± 5%</p> <p style="text-align: center;">17Kg ± 5%</p> <p style="text-align: center;">6mm ± 5%</p> <p style="text-align: center;">Pass</p> <p style="text-align: center;">LOW RADIUS of effect</p> <p style="text-align: center;">1.77 TOG</p> <p style="text-align: center;">33dB</p> <p style="text-align: center;">25000+</p> <p style="text-align: center;">HEAVY CONTRACT USE</p>	<p style="text-align: center;">TEST METHOD</p> <p style="text-align: center;">IMO Resolution A653 (16) IMO Resolution MSC61(67) Annex 1 Part 5 and Annex 2 IMO Resolution MSC61(67) Annex 1 Part 2 and Annex 2 BS 4790:1987 (2003)</p> <p style="text-align: center;">BS 4745: 1990/ISO 5085-1</p> <p style="text-align: center;">BS EN ISO 140- 8/ BS EN ISO 717-2</p> <p style="text-align: center;">BS 5808:1991(2005)</p>
<p>Disclaimer Whilst ever effort is made to ensure its accuracy, the data on this sheet is meant for information purposes only. The typical properties listed are the result of extensive laboratory tests, but since Carpenter has no control over the end use of each material, we cannot guarantee these results are obtained in practice. Users should conduct their own tests to determine the suitability of each material to its intended application. Note: Intrastat No: 3918900090</p>		